

Material Safety Data Sheet

Section 1: Chemical Product and Company Information	
Product Name Trade Name	Rubber Resin Bonded Abrasive Products Grinding Wheels or Stones
Manufacturer	Radiac Abrasives, Inc. 1015 S. College Avenue P.O. Box 1410 Salem, IL 62881
Phone Number Fax Number	618-548-4200 618-548-4207
Effective Date	October 30, 2009

Section 2: Composition/Information on Ingredients						
<i>May contain the following ingredients</i>						
Chemical Name	CAS #	ACGIH TLV	OSHA PEL	NIOSH	Carc. Y/N	Max. %
Aluminum Oxide	1344-28-1	10 mg/m ³	15 mg/m ³	NA	N	95
Silicon Carbide	409-21-2	10 mg/m ³	15 mg/m ³	10 mg/m ³	N	95
Cured Resin	NA	NA	NA	NA	N	16
Calcium Oxide	1305-78-8	2 mg/m ³	5 mg/m ³	2 mg/m ³	N	2.8
Iron Pyrites	12068-85-8	NA	NA	NA	N	3.9
Cured Rubber	78-79-5	NA	NA	NA	N	11.2
Wollastonite	13983-17-0	10 mg/m ³	10 mg/m ³	15 mg/m ³	N	6.1
Feldspar	68476-25-5	10 mg/m ³	5 mg/m ³	NA	N	4.5
Fluorspar	7789-75-5	2.5 mg/m ³	15 mg/cf	NA	N	10.6
Calcium Carbonate	471-34-1	10 mg/m ³	15 mg/m ³	10 mg/m ³	N	9.1
Graphite	7782-42-5	2 mg/m ³	15 mg/m ³	2.5 mg/m ³	N	1.5
Sulfur	7704-34-9	NA	NA	NA	N	1.3
Potassium Sulfate	7778-80-5	10 mg/m ³	15 mg/m ³	NA	N	10.2

HMIS Hazard Rating	
Health	0
Flammability	0
Reactivity	0
Personal Protection	E

Radiac Abrasives, Inc.

Section 3: Hazards Identification

Emergency Overview:	Dust may be irritating. May cause delayed lung damage. Low hazard to usual industrial or commercial handling.
Target Organs:	Respiratory System
Inhalation:	Grinding generates dust. Prolonged exposure to grinding dust may cause respiratory problems or aggravate existing conditions. Inhalation during grinding can cause coughing and shortness of breath. Consideration should also be given to the airborne concentration of the material being ground.
Eye Contact:	Dust generated during grinding may irritate eyes.
Skin Contact:	Excessive contact with dust may cause irritation.
Ingestion:	No known effects but ingestion is not recommended.
Other:	Some grinding operations may cause noise or vibration irritation. Grinding wheels are not a known carcinogen.

Section 4: First Aid Measures

Eyes:	Immediately flush with plenty of water. Get medical attention if irritation persists.
Skin:	Wash skin with soap and water. Get medical attention if irritation persists.
Inhalation:	Move to fresh air.
Other:	If hearing problems persist, obtain medical assistance if necessary.

Section 5: Fire Fighting Measures

Flash Point:	None
Flammable Limits:	None
Extinguishing Media:	Any media appropriate for the surrounding fire.
Fire Fighting Equipment:	Fire fighters should wear goggles and self-contained breathing apparatus to avoid inhalation of smoke or vapors.
Fire and Explosion Hazards:	None from this product. Consideration must be given to the potential fire/explosion hazards from the material being processed. Many materials create flammable/explosive dusts when ground.

Radiac Abrasives, Inc.

Section 6: Accidental Release Measures

Clean Up:	Use normal clean up procedures.
Disposal:	Dispose of in accordance with local, state and federal regulations.

Section 7: Handling and Storage

Handling:	Do not use at speeds greater than product was made to be used. Inspect wheel for damage on arrival and prior to mounting on machine. Avoid breathing dust. Avoid skin and eye contact with grinding dust. Use in well-ventilated area.
Storage:	Wheels should not be exposed to water or other solvents; any temperature or humidity condition that causes condensation on the wheels or freezing temperatures. See ANSI B7.1, 2.3.

Section 8: Exposure Controls/Personal Protections

Respiratory Protection:	Use NIOSH approved respirators as required to maintain exposure below Threshold Limit Values (TLV/TWA). See OSHA 29 CFR 1910.134.
Skin Protection:	Leather, cloth, rubber or vinyl gloves as desired by user.
Eye Protection:	Safety goggles or safety glasses with side shields are recommended. See OSHA 29 CFR 1910.133.
Hearing Protection:	See OSHA 29 CFR 1910.95 concerning hearing protection.
Engineering Controls:	Local exhaust ventilation as necessary to keep dust levels below Threshold Limit Values (TLV/TWA).
Other Precautions:	Visually inspect all wheels before mounting for possible damage. Do not operate above maximum operating speed. Always use a guard. Refer to ANSI B7.1 for the "Safety Requirements for the Use, Care and Protection of Abrasive Wheels."

Radiac Abrasives, Inc.

Section 9: Physical and Chemical Properties

Boiling Point:	NA
Vapor Pressure:	NA
Vapor Density:	NA
Specific Gravity:	1.5 – 3.1
Solubility in Water:	Very slightly
Freezing Point:	NA
Melting Point:	NA
pH:	Not relevant
Physical Form:	Solid
Color:	Various
Odor:	None

Section 10: Stability and Reactivity

Stability (Conditions to Avoid):	This is a stable material. Avoid overspeed and unsafe use conditions.
Incompatibility (Specific Materials to Avoid):	Avoid strong acids and bases.
Hazardous Polymerization:	Will not occur.
Hazardous Decomposition:	Dusts are generated in use. In most cases, dusts from the work piece will be significantly greater than from the grinding wheel. Coolants may produce other decomposition products.

Section 11: Toxicological Information

No Information Available

Radiac Abrasives, Inc.

Section 12: Ecological Information

No Information Available

Section 13: Disposal Considerations

Dispose of in accordance with local, state and federal regulations.

Section 14: Transport Information

Grinding wheels are not a DOT hazardous material.

Section 15: Regulatory Information

This product does not contain and was not manufactured with any Ozone Depleting Chemicals. This product is not subject to SARA 313 reporting.

Section 16: Other Information

The information and recommendations set forth are taken from sources believed to be accurate. Radiac Abrasives, Inc. makes no warranty with respect to the accuracy of this information or the suitability of these recommendations, assumes no liability to any user thereof. It is the responsibility of the user to investigate and understand pertinent sources of information to comply with all laws and procedures applicable to the safe use and handling of the product and to determine the suitability of the product for its intended use.